

## PRODUCT DATA    **HARD HAT® AEROSOLS MARKING PAINT 2300**

### DESCRIPTION

RUST-OLEUM® Hard Hat Aerosol Marking Paint 2300 is based on a fast drying short oil alkyd (2358 is based on an acrylic resin). The products are based on lead- and chromate free pigments.

### RECOMMENDED USES

RUST-OLEUM Marking Paint 2300 should be used on metal, concrete, asphalt, gravel, soil and grass, etc.

RUST-OLEUM Marking Paint 2300 is not water-soluble and should be used in light industrial exposures, normal humidity and interior applications.

RUST-OLEUM Marking Paint 2300 is designed for quick and easy marking of construction and excavation sites, underground utilities and for traffic safety.

### TECHNICAL DATA

Appearance: Flat  
Colour: See colour card  
Propellant: Dimethyl ether  
VOC-content: 630 - 670 g/l

**Drying times**    20°C/50% r.v.  
To touch: 20 minutes  
To handle: 4 hours  
To recoat: within 1 hour or after 48 hours  
Full hardness 7 days  
Heat resistance: 100°C (dry heat)

### Coverage

Theoretical: 2 m<sup>2</sup> per spray can at 25 µm dry, depending on colour.  
Practical: Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

### SURFACE PREPARATION

Remove dirt, grease, oil and all other surface contaminants by appropriate means. The surface must be clean and dry during application.

### DIRECTION FOR USE

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use.

Invert can and point spray button at ground or floor. Hold can approx. 10 - 15 cm above the surface to be marked. Press spray button to start spraying. Use a steady even stroke while spraying. After use turn can upright and press spray button for 2 - 3 seconds to clean valve.

### APPLICATION CONDITIONS

For good results the relative humidity shall be below 85% and the temperature of the can and substrate above 0°C.

### REMARKS

Fluorescent Marking Paint should be applied on a white substrate for maximum brightness.

### SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

### SHELLIFE / STORAGE CONDITIONS

3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

#### Rust-Oleum Netherlands B.V.

Braak 1, 4704 RJ  
P.O. Box 138, 4700 AC  
Roosendaal, The Netherlands  
T +31 (0)165 593 636  
F +31 (0)165 593 600  
[info.nl@ro-m.com](mailto:info.nl@ro-m.com)  
[www.ro-m.com](http://www.ro-m.com)

#### N.V. Martin Mathys S.A

Kolenbergstraat 23  
B - 3545 Zelem  
Halen, Belgium  
T +32 (0)13 460 200  
F +32 (0)13 460 201  
[info.be@ro-m.com](mailto:info.be@ro-m.com)  
[www.ro-m.com](http://www.ro-m.com)

#### Rust-Oleum France S.A

11, Rue Jules Verne, B.P. 39  
95322 St-Leu-la-Forêt Cedex  
France  
T +33 (0)130 400 044  
F +33 (0)130 409 980  
[info.fr@ro-m.com](mailto:info.fr@ro-m.com)  
[www.ro-m.com](http://www.ro-m.com)

#### Rust-Oleum UK Ltd.

Unit 5D, Alexandra Way  
Ashchurch B. Centre,  
Tewkesbury, Gloucestershire  
GL20 8NB, United Kingdom  
T +44 (0)1684 273 333  
F +44 (0)1684 273 331  
[info.uk@ro-m.com](mailto:info.uk@ro-m.com)  
[www.ro-m.com](http://www.ro-m.com)

#### Rust-Oleum Mathys Italia s.r.l.

Via Mazzetta 36, 13856  
Vigliano Biellese BI, Italia  
T +39 015 8122 160  
F +39 015 8122 161  
[info.it@ro-m.com](mailto:info.it@ro-m.com)  
[www.ro-m.com](http://www.ro-m.com)