

BIOSAN

AQUA MATT

TECHNICAL DATA SHEET

DATE : 08/03
ISSUE : 02
NUMBER : TE-112

► DESCRIPTION

Waterborne bactericidal matt acrylic paint.

► APPLICATION

For the interior coating of walls and ceilings in low wear areas where controlled hygienic conditions are of essential importance.

► FEATURES

High durability - perfect saponification resistance - particularly high covering capacity.
Helps to maintain a hygienic environment.

► TECHNICAL DATA

Binder	:	styrene acrylic resins
Finish	:	satın matt
Gloss (60°)	:	± 5
Colour (s)	:	white + mixing machine colours
Solids content (ASTM, D1644/a)	:	in volume : 47 – 50 % in weight : 62 – 65 %
Density (ASTM, D1475, 20°C)	:	1,3 – 1,4 g/cm ³
VOC-content (Volatile Organic Compounds)	:	max. 25 g/l
Consumption	:	7 - 10 m ² /l per coat
Thickness wet film	:	± 125 micron (cons.: 8 m ² /l)
dry film	:	± 60 micron (cons.: 8 m ² /l)
Drying times	:	± 40 minutes (10 m ² /l)
(for t° 20°C)	:	± 4 hours (10 m ² /l)
(for R.H. 60%)	:	± 1 day
Flashpoint (DIN53213)	:	not flammable

► INSTRUCTIONS FOR USE

Ambient conditions	:	minimum 5C / maximum 80 % R.H.
Dilution	:	If necessary, dilute with 5 % of water or Fair-Decor (for prolonged drying time).
Cleaning tools	:	water
Airless	:	Nozzle : 013 - 018 Pressure : 180 bars
Conventional spray-gun	:	Yes, dilute with water (3 - 5 %).
Brush	:	Apply with flat brush.
Roller	:	Apply with dispersion roller.
Particularities	:	The use of Biosan products does not exclude the necessity to clean and disinfect on a normal and regular basis.

► PREPARATION OF THE SUBSTRATE

The substrate must be sufficiently dry and stable; clean thoroughly.
On porous substrates apply first a coat of Parafix-Biosan Aqua Matt (1/1) or preferably Pegafix.
On very smooth bricks, apply a first coat of Noxyde diluted with 25 % water, or a coat of Pegalink.
Impregnate old chalking paints, after cleaning, with a coat of Fixonal or Pegafix.
Fill up holes and seal joints or fissures with Elastofill. If necessary, fill with Pegaflex.
Flat down and remove dust. Hereafter, apply 1 - 2 coats of Biosan Aqua Matt.

► ADDITIONAL INFORMATION

Transport codes	:	see MSDS
Packing	:	5 l
Storage stability	:	At least 24 months, provided the original tin is properly sealed and kept in a cool, dry and frostfree place.
AFNOR Classification	:	Group I, class 7b2

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, expressed, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.
"As for the precautions of use, hygiene and safety, please consult our Material Safety Data Sheets - available on request at our Technical Service".